

Galden PFPE: Heat Transfer Fluids

Product Data Sheet

Solvay Solexis offers a safe Heat Transfer (HT) media for demanding applications, including:

- **Semiconductor**
- **Chemical**
- **Pharmaceutical**
- **Vapor Phase Heating**
- **Transformer and Super Computer Cooling**
- **Recirculating Chillers**

Galden HT is a line of fluids with boiling points ranging from 55°C to 270°C and pour points from -115°C to -66°C. Galden HT fluids therefore cover a wider liquid range than other fluorinated heat transfer fluids, with typical use range temperatures exceeding 300°C.

G
A
L
D
E
N



Galden HT Fluids Application Chart

Industries	Applications	Benefits
Electronic	Direct Immersion	Compatibility (inert) High thermal stability
	Etcher (PVD, CVD)	Compatibility Dielectric Low viscosity at low temperatures Dielectric (non-conductive) Non-flammable
	Ion Implanter	High resistivity Environmentally safe
	Radar	Compatibility Thermal and oxidative stability
Electrical	Transformer Power Supplies	Non-flammable Environmentally safe Excellent dielectric properties
Nuclear	UF6 Production	Low viscosity Good radiation resistance
Chemical	Aggressive Conditions	High chemical and thermal stability, Inert Oxidative stability
Pharmaceutical	Freeze Dryer	Non-flammable Low temperature viscosity

For information contact your Solvay Solexis representative or:

Europe
Solvay Solexis S.p.A. (Italy)
Tel: +39-02-3835-1
Fax: +39-02-3835-2129
Email: solvaysolexis.ita@solvay.com

North America
Solvay Solexis, Inc.
Tel: +1-856-853-8119
Fax: +1-856-853-6405
Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2002, Solvay Solexis, Inc. All Rights Reserved.

Galden PFPE: Heat Transfer Fluids

Product Data Sheet

The following properties are equal for all Galden Heat Transfer grades:

Typical Property	Units	All Galden HT Grades
Specific Heat, 25°C	cal/g°C	0.23
Thermal Conductivity, 25°C	W/cm°C	0.0007
Coefficient of Expansion	cm ³ /cm ³ °C	0.0011
Dielctric Strength, 25°C	KV (2.54 mm gap)	40
Dissipation factor, 25°C (1Khz)	—	2x10 ⁻⁴
Solubility of Water	ppm(wt)	14
Solubility of Air	cm ³ gas/100cm ³ liquid	26

Galden HT Fluids

Available Grades and Typical Physical Properties

Typical Properties	Units	HT55	HT70	HT90	HT110
Boiling Point	°C	57	70	90	110
Pour Point	°C	<-110	<-110	<-110	<-110
Density, 25°C	g/cm ³	1.65	1.68	1.69	1.72
Kinematic Viscosity, 25°C	cSt	0.45	0.50	0.75	0.83
Kinematic Viscosity, 0°C	cSt	0.64	0.75	1.14	1.21
Kinematic Viscosity, -20°C	cSt	0.91	1.09	1.75	1.94
Kinematic Viscosity, -40°C	cSt	1.40	1.79	3.12	3.74
Vapor Pressure, 25°C	torr	224	141	48	12
Heat of Vaporization @ Boiling Point	cal/g	22	17	17	17
Refractive Index, 25°C	—	1.280	1.280	1.280	1.280
Surface Tension, 25°C	dynes/cm	10	14	16	16
Average Molecular Weight	—	340	410	460	580
Dielectric Constant 25°C (1Khz)	—	1.86	1.86	1.90	1.90
Volume Resistivity	Ohm-cm	1x10 ¹⁵	1x10 ¹⁵	1x10 ¹⁵	1x10 ¹⁵

For information contact your Solvay Solexis representative or:

Europe
Solvay Solexis S.p.A. (Italy)
Tel: +39-02-3835-1
Fax: +39-02-3835-2129
Email: solvaysolexis.ita@solvay.com

North America
Solvay Solexis, Inc.
Tel: +1-856-853-8119
Fax: +1-856-853-6405
Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2002, Solvay Solexis, Inc. All Rights Reserved.

Galden PFPE: Heat Transfer Fluids

Product Data Sheet

Available Grades and Typical Physical Properties

Typical Properties	Units	HT135	HT170	HT200	HT230	HT270
Boiling Point	°C	135	170	200	230	270
Pour Point	°C	<-100	-97	-85	-77	-66
Density, 25°C	g/cm ³	1.73	1.77	1.79	1.82	1.85
Kinematic Viscosity, 25°C	cSt	1.0	1.8	2.4	4.4	14.0
Kinematic Viscosity, 0°C	cSt	2.40	3.41	4.97	12.00	48.0
Kinematic Viscosity, -20°C	cSt	2.92	7.11	11.65	34.00	—
Kinematic Viscosity, -40°C	cSt	6.32	21.14	—	—	—
Vapor Pressure, 25°C	torr	8	<1	<1	<1	<10 ⁻²
Heat of Vaporization @ Boiling Point	cal/g	16	16	15	15	15
Refractive Index, 25°C	—	1.280	1.280	1.281	1.283	1.283
Surface Tension, 25°C	dynes/cm	17	18	19	19	20
Average Molecular Weight	—	610	760	870	1020	1550
Dielectric Constant 25°C (1Khz)	—	1.90	1.90	1.94	1.94	1.94
Volume Resistivity	Ohm-cm	6x10 ¹⁵	6x10 ¹⁵	6x10 ¹⁵	6x10 ¹⁵	6x10 ¹⁵

G
A
L
D
E
N[®]

For information contact your Solvay Solexis representative or:

Europe

Solvay Solexis S.p.A. (Italy)

Tel: +39-02-3835-1

Fax: +39-02-3835-2129

Email: solvaysolexis.ita@solvay.com

North America

Solvay Solexis

Tel: +1-856-853-8119

Fax: +1-856-853-6405

Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2002, Solvay Solexis, Inc. All Rights Reserved.